

**Description**


One component moisture curing acetic silicone sealant by reaction. Suitable for sealing gear boxes, pumps, motors and compressors flanges, hot fluid pipes. Provides an extremely flexible gasket between surfaces and resists to vibrations, thermal shocks, water, gas, LPG, oils and several chemicals. Keeps its sealing properties within temperatures of - 60° and + 250°C with peaks up to 300 °C. Sealed parts can be disassembled using normal tools.

**Physical properties**

Composition : silicon acetic curing  
Colour : red/black  
Physical appearance : paste  
Specific weight (g/ml) : 1,0 - 1,1  
Shelf life : 1 year at +25°C in original unopened packaging

**Depth of cure**

The graph below shows the depth of cure of the product (mm) vs. time (h)  
Test done at +23°C - H.R. 50%

**Curing properties**

Track free time : 10 - 20 min  
Handling time : 1 - 2 hours  
Functional cure time : 2 - 4 hours  
Full cure time : 12 - 24 hours

**Typical properties after 7 days/ +23°C/ UR 50%**

Hardness - Shore A (ASTM 2240) : 32 ± 5 Shore A  
Tensile strength (ASTM D-412) : 2,5 MPa  
Elongation at break (ASTM D-412) : 300% - 600%  
Modulus - Young : 0,4 MPa  
Compression modulus (ASTM D-575) : 2,2 Mpa  
Coefficient of thermal expansion (%/°C) : 0,05  
Temperature range : -60°C/+250°C – peaks +300°C

**Directions for use**

Clean and degrease parts to bond with Loxeal Cleaner 10. Apply enough product to fill the gap. The product is moisture curing therefore pieces shall be assembled rapidly. Allow full cure before putting stress on pieces assembled.

**Storage**

Keep product in a cool and dry room at +25°C. To avoid contaminations do not refill containers with used product. For more information on applications, storage and handling contact Loxeal Technical Service

**Safety and handling**

Consult Material Safety Data Sheet before use.

**Note**

The data contained herein, obtained in Loxeal laboratories, are given for information only; if specifics are required, please contact Loxeal Technical Department. Loxeal ensures abiding quality of supplied products according to its own specifics. Loxeal cannot assume responsibility for the results obtained by others which methods are not under Loxeal control. It is user's responsibility to determine suitability for user's purpose of any product mentioned herein. Loxeal disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loxeal products. Loxeal specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.